

klöckner & co multi metal distribution

E-mail: DAVID.BASES@cdl.es

Fecha: 6/04/10

Medida	Orden Fabric.	Norma fabric.	Calidad del acero	Esp	Rec	Ensayos Mecánicos				Ensayos Químicos %									
						Rp.0.2 MPa	Rm MPa	A%	HRB	C	Mn	Si	P	S	Nb	V	Cr	Ni	Al
TCS-30X30X1,5/6000 D DD11	96105	UNE10305-5	DD11			265,0	336,0	32,60		0,035	0,234	0,018	0,017	0,018					0,042
TCS-40X40X1,5/6000 D DD11	96358	UNE10305-5	DD11			178,0	303,0	39,00		0,031	0,220	0,016	0,022	0,015					0,044
TRS-30X15X1,5/6000 D DD11	96409	UNE10305-5	DD11			265,0	336,0	32,60		0,035	0,234	0,018	0,017	0,017					0,041
TCS-50X50X2/6000 D S235JR	96828	UNE10305-5	S235JR			353,0	456,0	22,80		0,110	0,530	0,010	0,020	0,016					0,021
Observaciones									Firmado			 David Bases (Departamento de Calidad)							